

Exolon® UV

Patterned polycarbonate sheet



Your benefits:

- excellent weathering resistance
- extreme impact strength
- resistance to a wide range of temperatures

Exolon® UV patterned sheets are clear transparent polycarbonate sheets with UV protection on both sides, and a patterned surface. They offer extreme impact strength that exceeds the physical properties of other products of their class.

Exolon sheets resist temperatures of -100 to +120 °C.

Exolon® UV clear 2099 RH is a clear transparent sheet with high light transmission, a raindrop pattern on one side, and a haircell pattern on the other side.

Applications:

Typical applications for **Exolon® UV** patterned sheets include lighting fixtures, luminair covers, balcony guards, wall and door partitions. The sheets offer protection against involuntary breakage and wilfull destruction. The patterned surfaces offer a solution wherever sight screens are required to let in light.

	Test Conditions	Typical values ⁽¹⁾	Unit	Standard
PHYSICAL				
Density	water at 23 °C	1200	kg/m ³	ISO 1183-1
Water absorption saturation	23 °C, 50% relative humidity	0.30	%	ISO 62
Water absorption equilibrium	Procedure A	0.12	%	ISO 62
Refractive index		1.587	-	ISO 489
MECHANICAL				
Tensile modulus	1 mm/min	2350	MPa	ISO 527-1,-2
Yield stress	50 mm/min	> 60	MPa	ISO 527-1,-2
Yield strain	50 mm/min	6	%	ISO 527-1,-2
Strain at break	50 mm/min	120	%	ISO 527-1,-2
Flexural modulus	2 mm/min	2350	MPa	ISO 178
Flexural strength	2 mm/min	90	MPa	ISO 178
Charpy impact strength	23 °C, unnotched	non-break	kJ/m ²	ISO 179-1eU
Charpy impact strength	23 °C, 3 mm, notched	80P	kJ/m ²	ISO 179-1eA
Izod impact strength	23 °C, 3.2 mm, notched	70P	kJ/m ²	ISO 180-A
THERMAL				
Vicat softening temperature	50 N, 50°C/h	148	°C	ISO 306
Thermal conductivity	23°C	0.20	W/(m.K)	ISO 8302
Coefficient of linear thermal expansion	23 to 55°C	0.65	10 ⁻⁴ /K	ISO 11359-1, -2
Temperature of deflection under load	1.80 Mpa	128	°C	ISO 75-1, -2
Temperature of deflection under load	0.45 Mpa	140	°C	ISO 75-1, -2
ELECTRICAL				
Electrical strength	1 mm	34	kV/mm	IEC 60243-1
Volume resistivity		1E14	Ohm.m	IEC 60093
Surface resistivity		1E16	Ohm	IEC 60093
Relative permittivity	100 Hz	3.1	-	IEC 60250
Relative permittivity	1 MHz	3.0	-	IEC 60250
Dissipation factor	100 Hz	5 10 ⁻⁴	-	IEC 60250
Dissipation factor	1 MHz	95 10 ⁻⁴	-	IEC 60250

⁽¹⁾ These values are measured on injection molded samples, and are not intended for specification purposes.

Exolon® UV

Patterned polycarbonate sheet



Exolon Group S-Line, the standard product line, represents a range of certified quality products which offer the reliable solution for most applications.

Light Transmission: Test Method according to DIN 5036.

The stated thicknesses are not all available as standard. Please ask us for more information.

The stated values are typical values only.

Light transmission in % at 3 mm thickness	Exolon® UV RH
clear 2099	86
green 2650	67
blue 2550	53
bronze 2850	44

Available sizes: Exolon® UV patterned sheets are available in thicknesses 3 – 6 mm and in following sizes; other sizes, colors and sheet thicknesses on request.

Colors:

Exolon® UV green 2650 R

Exolon® UV bronze 2850 RH

Exolon® UV blue 2550 RH

Exolon® UV clear 2099 RH

Patterns:

Exolon® UV clear 2099 RH



Sizes (Standard):

3,050 x 2,050 mm (RH)

Weathering Resistance: Exolon® UV sheets show excellent weathering resistance, which guarantees their impact strength even after many years. Since their introduction in 1989, the sheets have been examined in an intensive test program, including a real-time outdoor exposure test in a southern European climate (Bandol).

Permanent Service Temperature: The permanent service temperature without load is approx. 120 °C.

Fire Rating ^(*):

Country	Standard	Rating	Thickness	Color
Europe	EN13501	B s1 d0	3 - 6 mm	clear 2099 RH

*) Fire certificates could be limited in time and scope, always check if the mentioned certificate is valid for the purchased Polycarbonate sheet type at the date of delivery. Polycarbonate sheets may change their fire behavior due to ageing and weathering. The indicated fire rating was tested on new / unweathered Product in accordance with the indicated fire classification standards.

Glow wire flammability index, IEC 60695-2-12, in °C ^(*): Exolon® UV clear 2099 RH: 960 °C at 3 mm



Exolon Group NV
Wakkensesteeweg 47
8700 Tielt

Belgium

www.exolongroup.com
sales@exolongroup.com

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance, information and recommendations to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by Exolon Group. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.

Makrolon® is a registered trademark, owned and licensed by Covestro Group